



(The Gold Series) Plural, 1.7 pound Insulating Spray Foam

DESCRIPTION

SPEC Technologies 1.7 GOLD is an **HFC 245 fa** blown, liquid spray system which cures to a low density rigid polyurethane insulation developed for application to sidewalls, cavity fill and tanks at substrate temperatures as low as minus 40°F (4°C). It is available in three reactivity variations to meet a broad range of surface temperature conditions.

SPEC Technologies 1.7 GOLD has undergone preliminary testing and should meet a Class I Fire Rating standard. Polyurethane foam used on the interior of a structure intended for human occupation must be protected by an approved 15 minute thermal barrier. When used on the exterior of structures and on structures that are not intended for human occupation these restrictions do not apply. Please check local codes for further information. When exposed to open flame, cured polyurethane foam may present a serious fire hazard.

Product Description

SPEC Technologies 1.7 GOLD is a fast set polyurethane spray insulation system. **SPEC Technologies 1.7 GOLD** is a premium construction product, and is environmentally friendly. It exhibits superior insulation properties compared to other conventional insulation materials. **SPEC Technologies 1.7 GOLD** meets the highest flame retardancy standards for construction materials. **SPEC Technologies 1.7 GOLD** is easy to apply and its fast reaction time allows the contractor to complete difficult jobs quickly.

Uses

SPEC Technologies 1.7 GOLD is a superior insulation material designed specifically for residential and commercial construction projects. **SPEC Technologies 1.7 GOLD** is flexible, accommodating movement of the substrate. **SPEC Technologies 1.7 GOLD** is designed interior applications only. **SPEC Technologies 1.7 GOLD** is recommended for new construction and retrofit of existing structures.

Advantages

Fast set, allows quick job turn-around, contains no Ozone Depleting substances. Seamless, expands to fill voids and prevents air movement. Flexible, allows for some building movement. Excellent Thermal Stability, and dimensional stability, will not shrink under adverse weather conditions. Odorless, No Toxic Vapors after application, Class I Fire Retardancy rating.

Limitations

SPEC Technologies 1.7 GOLD should not be used for exterior applications as the sunlight will rapidly degrade foam. It should not be used where foam will stay submerged in water. Applicable codes must be strictly adhered to.

Typical Liquid Properties

<u>PROPERTY</u>	<u>TEST METHOD</u>	<u>TYPICAL VALUE</u>
Viscosity "A"	ASTM D-2196	200-250 cps @ 77°F
Viscosity "B"	ASTM D-2196	350-400 cps @ 77°F
Weight Per Gallon "A"	ASTM D-1475	10.20 LBS/Gallon
Weight Per Gallon "B"	ASTM D-1475	9.80 LBS/Gallon

Typical Reactivity

Cream time 3-4 seconds @ 25°C
 Rise Time 12-16 seconds @ 25°C

Typical Physical Properties

<u>PROPERTY</u>	<u>TEST METHOD</u>	<u>TYPICAL VALUE</u>
Density	ASTM D-1622	1.70±0.10 Lbs/ft ³
k-Factor	ASTM C-177	.219 BTU in/°F
R-Value	ASTM C-518	6.75 °F/BTU in
Flame Spread Index	ASTM E-84-1"	<20
Smoke Generation Index	ASTM E-84-1'	<200
Water Vapor Transmission	ASTM E96-95	2.55 Perm Inch
Dimensional Stability	ASTM D-2126-94	00.3 % 28 Day, 158°F, 97% RH
Service Temp Range		-40 to 200 degrees F
Water Absorbtion Rate		0.055 lbs/ sq ft, 2" head
Tensile Strength	ASTM D-1623-78	25 PSI
Parallel to rise	C-273-94	21 PSI
Closed Cell Content	D-2856C-4	90% by volume

Winter regular and summer grades available

Packaging

One Thousand Pound Kit: 500 Pounds of 'A' side and 500 Pounds of 'B' side.
 One Hundred Pound Kit: 50 Pounds of 'A' side and 50 Pounds of 'B' side.

Mixing

Prior to designing and installing a spray polyurethane foam interior insulation system, code officials should be consulted for recommendations and approvals. Federal, local and state building codes vary. All require that spray applied polyurethane foam insulation be covered with an approved 15 minute fire rated thermal barrier. One typically approved material is ½" (1 cm) gypsum wallboard applied over the spray polyurethane foam insulation. However, always check with local officials for recommendations and approvals. It is recommended that the approved thermal barrier be installed the same day the foam is applied.

All hot work, i.e., welding, torches and open flame work, must have been completed prior to commencing the installation of the polyurethane foam insulation. Smoking in the same area while the spray polyurethane foam insulation is being applied shall be strictly prohibited.

SPEC Technologies 1.7 GOLD cannot be applied when substrate temperatures are below 40°F (4°C). Ambient conditions, component temperatures, spray gun mix efficiency and foam thickness also influence reactivity. Technical Service Personnel should be consulted whenever conditions are marginal. The aforementioned information on this product is to be used as a guide and is subject to change without notice. They are offered in good faith, but without guarantee, as conditions and methods and use of our products are beyond our control. Any obligation of the seller or manufacturer shall have no force or effect unless it is in writing and signed by officers of the manufacturer.

SPEC Technologies 1.7 GOLD must be spray applied using approved equipment. Use 1:1 ratio pump, with appropriate material heaters, as required for individual application.

Minimum Parameters for Processing SPEC Technologies 1.7 GOLD

Working Pressure 1000-1500 psi
 Working Temperature 120-140 °F

TYPICAL PHYSICAL PROPERTIES

Properties shown are for materials sprayed onto a surface at room temperature and removed for physical

testing. The values presented were derived from polyurethane foam, which was adequately mixed and properly metered at the specific ratio. If the polyurethane foam is not adequately mixed and properly metered at the specified ratio, the resulting values will not conform to the listed specifications.

Prior to designing and installing a spray polyurethane foam interior insulation system, code officials should be consulted for recommendations and approvals. Federal, local and state building codes vary. All require that spray applied polyurethane foam insulation be covered with an approved 15 minute fire rated thermal barrier. One typically approved material is ½" (1 cm) gypsum wallboard applied over the spray polyurethane foam insulation. However, always check with local officials for recommendations and approvals. It is recommended that the approved thermal barrier be installed the same day the foam is applied.

All hot work, i.e., welding, torches and open flame work, must have been completed prior to commencing the installation of the polyurethane foam insulation. Smoking in the same area while the spray polyurethane foam insulation is being applied shall be strictly prohibited.

SPEC Technologies 1.7 GOLD cannot be applied when substrate temperatures are below 40°F (4°C). Ambient conditions, component temperatures, spray gun mix efficiency and foam thickness also influence reactivity. Technical Service Personnel should be consulted whenever conditions are marginal. The aforementioned information on this product is to be used as a guide and is subject to change without notice. They are offered in good faith, but without guarantee, as conditions and methods and use of our products are beyond our control. Any obligation of the seller or manufacturer shall have no force or effect unless it is in writing and signed by officers of the manufacturer.

The information herein is believed to be reliable but unknown risks may be present. ALL WARRANTIES OF ANY KIND, EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND THAT GOODS ARE OF MERCHANTABLE QUALITY, ARE SPECIFICALLY DISCLAIMED. Contact SPEC Technologies for information concerning its limited warranty and its availability.

Disclaimer: The data presented herein is not intended for use by nonprofessional applicators, or those who do not purchase or utilize this product in the normal course of their business. The potential user must perform any pertinent tests in order to determine the product's performance and suitability in the intended application, since final determination of fitness of the product for any particular use is the responsibility of the buyer.

This information and technical advice provided herein are believed to be reliable and accurate to the best knowledge of SPEC Technologies Inc. as based on tests and should serve only as recommendation. As the seller, SPEC Technologies Inc. makes no representation or warranties of any kind, expressed, implied or statutory, including but not limited to all implied warranties of merchantability or fitness for use or a particular purpose for the product. SPEC Technologies Inc. makes no representations or warranties as to the result of the use of the product and assumes no obligation or liability in the connection therewith. SPEC Technologies Inc. is not liable for any incidental or consequential damages of any sort from the use of this product. The information provided herein is subject to change at any time without notice. Information changes may include, but are not limited to, commercial and technical changes, changes in pricing, Physical characteristics and packaging.

All guarantees and warranties as to the products supplied by SPEC Technologies Inc. shall have only those guarantees and warranties expressed by the manufacturer. The buyer's sole remedy as to the material claims will be against the manufacturer of the product. The aforementioned data on this product is to be used as a guide and is subject to change without notice. The information herein is believed to be reliable, but unknown risks may be present. NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING PATENT WARRANTIES OR WARRANTIES OF MERCHANTABILITY OR FITNESS FOR USE, ARE MADE BY manufacturer. WITH RESPECT TO PRODUCTS OR INFORMATION SET FORTH HEREIN. Nothing contained herein shall constitute a permit or recommendation to practice any invention covered by a patent without a license from the owner of the patent. Accordingly, buyer assumes all risks whatsoever as to the use of these materials, and buyer's exclusive remedy as to any breach of warranty, negligence, or other claim shall be limited to the purchase price of the materials. Failure to adhere to any recommended procedures shall relieve SPEC Technologies Inc. and the manufacturer of all liability with respect to the materials and their use thereof.